

ISO 9001:2000, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER 052133

HEAT NUMBER **A00750** SALES ORDER / RLS **031171 / 5** CERT ID / REV **00013320 / 01**

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

| CUSTOMER P.O. CUSTOMER PART | | | | | QUANTITY COILS LADING NO 5,564 lbs 2 00042544 | | | SHIPMENT DAT 04/23/2010 | |
|-----------------------------|-------------|-------------------------|--------------------------|-------------|--|---------------------|-------------|-----------------------------------|-------------------------|
| SPECIFICATIO | | 018130-08 8 IQ, Clea | n/Coat, Cle | ean/Phos/I | _ube, Winc | lsor Machi | ine & Stan | nping Ltd, 7 | 213.91.6000 |
| CUSTOMER RE | QUIREMEN | rs | | | | | | | |
| | | | | Chemical | (value of § | 9 = n/a) | | | |
| C .1500 | Mn .6800 | P .0090 | s .0050 | si .2600 | Cu .1800 | Ni .0600 | Cr .1200 | Мо .0170 | Sn Al .0090 .0040 |
| B .0000 | v .0020 | N .0075 | | | | | | | |
| | | | | Mechan | ical - Sum | mary | | | |
| <u>TEST</u> Diameter (in | ich) | | <u>JNITS</u> n | | | <u>HIGH</u> .512 | | <u>LOW</u> .511 | <u>AVERAGE</u> 0.512 |
| Tensile (psi) | | psi | | | | 76060 | | 73822 | 74941 |
| | | | | End of | f Certification | | | | |
| | | | | | | | | | |
| | | | | | | | | | |
| | | | | | | | | | |
| | | | | | | | | | |
| | | | | | | | | | |
| | | | | | | | | | |
| | | | | | | | | | |

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

