

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

## SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

## **Physical Test Report**

WORK ORDER **058719** 

HEAT NUMBER **A03213** 

SALES ORDER / RLS 035614 / 2 CERT ID / REV 00019428 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

					10,032 lbs 3 0004		5353 11/23/2010		/23/2010		
SPECIFICATION 13.00mm (0.5		018130-08 8 IQ, Cleai	n/Coat, Cle	ean/Phos/L	_ube, Wind	sor Mach	ine & Stam	ping Ltd, 7	<b>7213.91.6</b> 0	000	
CUSTOMER RE	QUIREMENT	S									
				Chemical	(value of 9	= n/a)					
.2000	Mn .8400	P .0090	s .0090	si .2200	Cu .1000	Ni .0500	Cr .1300	Mo .0160	Sn .0080	Al .0040	
B .0000	v .0010	N .0062									
				Mechan	ical - Sumı	mary					
TEST Diameter (inch)			<u>JNITS</u> <b>n</b>			<u>нідн</u> . <b>512</b>		<u>LOW</u> .510		<u>AVERAGE</u> <b>0.511</b>	
Tensile (psi)		ı	osi			78806		75765		77690	
				End of	Certification						

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Graham Benoit, QA Manager