

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER **059303**

HEAT NUMBER A03430

SALES ORDER / RLS 035981 / 4 CERT ID / REV 00019835 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

CUSTOMER P.O. CUSTOMER PART				QUAN 3,306						
SPECIFICATION 13.00mm (0.	•	018130-08 8 IQ, Clea	n/Coat, Cle	ean/Phos/L	_ube, Wind	sor Mach	ine & Star	nping Ltd, 7	7213.91.60	000
CUSTOMER RE	QUIREMENT	ΓS								
				Chemical	(value of 9) = n/a)				
.1800	Mn .6700	P .0150	s .0130	si .2000	Cu .2100	Ni .0700	Cr .1400	Mo .0230	Sn .0110	Al .0050
.0000	v .0020	N .0064								
				Mechan	ical - Sum	mary				
TEST Diameter (inch)		<u>UNITS</u> in				<u>нідн</u> . 509		<u>LOW</u> .509		<u> 0.509</u>
Tensile (psi)		psi				76167		76167		76167
				End of	* Certification					

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Graham Benoit, QA Manager