

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER **058720**

HEAT NUMBER **A03615**

SALES ORDER / RLS 035615 / 3 CERT ID / REV 00019420 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States

Attn: Quality Assurance

JSTOMER P.C). C	CUSTOMER P.	ART	QUANTITY 13,102 lbs			LADING NO SHIPMENT D 00045317 11/23/2010			
PECIFICATION 5.00mm (0.5	5900") 101	•		an/Lime (M	IOD), Winds	or Machine	e & Stan	nping (US,	7213.99.0	030
JOINER REC	ZOINLINI		(Chemical (value of 9 =	n/a)				
C .16	Mn .65	P .013	s .013	si .20	Cu .20	Ni .07	Cr .12	Mo .020	Sn .010	Al .005
B .0000	v .000	N .0061								

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Graham Benoit, QA Manager