

ISO 9001:2000, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER **048862**

LOT NUMBER **A98030**

SALES ORDER / RLS 028927 / 2 CERT ID / REV 00010905 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

SUSTOMER P.C	O. CUSTOMER PART Polymer				QUANT 9,758 I		OILS LADIN 3 0004			IPMENT DAT /20/2010
SPECIFICATION 0.5650" (14.3 Non-Alloy W C=>0.25% ar	35mm) 154 ire, Heat 1	reated	-	/Phos/Poly	ymer, Winds	sor Mach	ine & Star	mping Ltd,	7217.10.80	010
SUSTOMER RE	QUIREMENT	ΓS								
				Chemical	(value of 9	= n/a)				
.3700	Mn 1.4500	P .0120	s .0100	si .2200	Cu .1700	Ni .0600	Cr .0900	Mo .0180	sn .0080	Al .0050
B .0002	v .0050	N .0070								
				Mechan	ical - Summ	ary				
<u>rEST</u> Diameter (inch)			<u>UNITS</u> in			<u>нідн</u> .566		<u>LOW</u> .565		
Гensile (psi)		ı	psi			75389		73394	74214	

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Graham Benoit, QA Manager