

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER **069750**

HEAT NUMBER A06977

SALES ORDER / RLS 043290 / 3 CERT ID / REV 00029925 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States

Attn: Quality Assurance

CUSTOMER P.O. CUSTOMER PART								LADING NO 00050120		SHIPMENT DATE 11/29/2011	
SPECIFICATION 15.00mm (0.4) Hot Rolled R	5906") 101								9.0030		
CUSTOMER RE	QUIREMENT	гs									
				Chemical	(value of 9) = n/a)					
C .1700	Mn .6600	.0130	s .0150	si .2200	Cu .2000	Ni .0800	Cr .1000	Mo .0250	Sn .0080	Al .0040	
.0000	v .0020	N .0098									
				Mechan	ical - Sum	mary					
TEST Diameter (inch)		<u>UNITS</u> in				<u>нідн</u> .586		<u>LOW</u> .586		<u>AVERAGE</u> 0.586	
Tensile (psi)		psi				74898		74898		74898	
				End of	f Certification						

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Gary Allard, QA Manager