

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER **070407**

HEAT NUMBER **A07342**

SALES ORDER / RLS 043757 / 5 CERT ID / REV 00030793 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

CUSTOMER P.O. CUSTOMER PART				QUAN 4,148			LS LADING NO 2 00050461		SHIPMENT DATI 01/04/2012	
SPECIFICATIO 14.30mm (0. Hot Rolled F	5630") 101		n/Coat, Cle					(US, 7213.9 or Not	9.0030	
CUSTOMER RE	EQUIREMENT	rs								
				Chemical	(value of 9) = n/a)				
C .1600	Mn .7200	P .0070	s .0140	si .2200	Cu .2200	Ni Cr .0700 .1100		Mo .0330	Sn .0100	Al .0040
.0000	v .0010	N .0075								
				Mechan	ical - Sum	mary				
TEST Diameter (inch)		<u>UNITS</u> in				<u>нідн</u> .560		<u>LOW</u> .560	<u>AVERAGE</u> 0.560	
Tensile (psi)		i	osi			72270		72270		72270
				End of	Certification					

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Gary Allard, QA Manager