

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

**Physical Test Report** 

WORK ORDER **072120** 

HEAT NUMBER **A07588** 

SALES ORDER / RLS 044993 / 4 CERT ID / REV 00032364 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

CUSTOMER RE	EQUIREMENT	-S								
				Chemical	(value of 9	) = n/a)				
.1000	Mn .5000	P .0090	s .0170	si .1500	Cu .2100	Ni .0700	Cr .0800	Mo .0210	Sn .0100	Al .0010
.0000	v .0000	N .0074								
				Mechan	ical - Sumi	mary				
TEST Diameter (inch)		<u>UNITS</u> <b>in</b>				<u>нідн</u> . <b>491</b>		<u>LOW</u> .488	<u>AVERAGE</u> <b>0.490</b>	
Tensile (psi)		psi				63391		63102	63247	
				End of	Certification					

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Gary Allard, QA Manager