

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

**SIVACO Ontario** a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

## **Physical Test Report**

WORK ORDER 074159

HEAT NUMBER A07926 SALES ORDER / RLS 046500 / 3 CERT ID / REV 00034611 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

CUSTOMER P.O. CUSTOMER PART					QUANTITY <b>12,354 lbs</b>		OILS LADIN 6 00052		SHIPMENT DATE 05/03/2012	
SPECIFICATION 13.50mm (0. Hot Rolled R	5315") 101		n/Coat, Cle					(US, 7213.9	1.6000	
CUSTOMER RE		ſS								
				Chemical	(value of 9	) = n/a)				
C .1000	Mn .4800	Р .0070	s .0130	si .1000	Cu .1600	Ni .0600	Cr .0700	Мо .0250	Sn .0100	Al .0030
В .0001	v .0010	N .0077								
				Mechan	ical - Sum	mary				
<u>TEST</u> Diameter (inch)			<u>JNITS</u> i <b>n</b>			<u>HIGH</u> .533		<u>LOW</u> .528	<u>AVERAGE</u> 0.530	
Tensile (psi)		psi				62100		60290		61266
				End of	f Certification					

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Gary Allard, QA Manager