

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER 076978

HEAT NUMBER A10068 SALES ORDER / RLS 048601 / 4 CERT ID / REV 00037827 / 02

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

CUSTOMER P.C	OMER P.O. CUSTOMER PART				QUANTIT 8,332 lbs			SHIPMENT DATE 08/29/2012		
SPECIFICATION 15.00mm (0.5 Hot Rolled R	5906") 101								9.0030	
CUSTOMER REG	QUIREMENT	ſS								
			C	Chemical (value of 9 = r	n/a)				
C .17	Mn .64	P .012	s .017	Si .22	Cu .19	Ni .06	Cr .09	Mo .015	Sn .011	Al .004
в .0000	v .000	N .0077								
				Mechanic	cal - Summar	у				
<u>TEST</u> Diameter (inch)		<u>U</u> ii	<u>INITS</u> N			<u>нідн</u> .591		<u>LOW</u> .586	<u>AVERAGE</u> 0.588	
Tensile (psi)		p	si			73786		72548	73230	
				End of C	Certification					

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Gary Allard, QA Manager Q