

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER **074516**

HEAT NUMBER W28941

SALES ORDER / RLS 046175 / 3 CERT ID / REV 00035206 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

CUSTOMER P.	O. (CUSTOMER PART		QUAN ⁻ 4,352			DILS LADIN 2 0005			PMENT DAT 23/2012
7213.99.003	.5630") 101 0		Clean/Co	·	Phos/Polym (0.748"), F	·		ne & Stamp	ing (US,	
CUSTOMER RE	QUIREMEN ⁻	TS								
				Chemical	(value of 9	= n/a)				
C .1800	Mn .7500	P .0110	s .0010	si .1000	Cu .0400	Ni .0700	Cr .0600	Mo .0040	Sn .0020	Al .0490
B .0001	v .0060	N .0048								
				Mechan	ical - Sumn	nary				
<u>TEST</u> Diameter (inch)		<u>UNITS</u> in				<u>нідн</u> .562		<u>LOW</u> .562	<u>AVERAGE</u> 0.562	
Tensile (psi)		ı	psi			68924		68924		68924
				End of	f Certification					

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Gary Allard, QA Manager